

CLAIMS

- 5 1. A retortable sealant composition comprising :
- i) at least a copolymer of propylene and α -olefins, and
 - ii) at least a copolymer of ethylene and alkyl acrylate,
 wherein the alkyl acrylate is present in an amount ranging
10 from about 1 to less than 9 weight percent, relative to the
 weight of the sealant composition.
2. The composition of claim 1, wherein the alkyl acrylate is present in
 an amount ranging from about 1 to about 6 weight percent, relative to
 the weight of the sealant composition.
- 15 3. The composition of claim 1, wherein the alkyl acrylate is selected
 from methyl acrylate and butyl acrylate.
4. The composition of claim 1, wherein the copolymer of propylene
 and α -olefins shows a melting point less than 155°C measured
 according to ASTM D 3418.
- 20 5. The composition of claim 1, wherein the copolymer of propylene
 and α -olefins is selected from random copolymers of propylene and
 ethylene and terpolymers of propylene, ethylene and butene.
6. Retortable multilayer film comprising at least one substrate layer
 and at least one sealant layer comprising the sealant composition of
25 claim 1.
7. Retortable packaging comprising the retortable sealant composition
 of claim 1.